

# COTTON CUTS FOR CROCKMETER<sup>+</sup>

For Assessing the Colour Fastness to Rubbing

For tests according to:  
<sup>+</sup> ISO 105-X12:2016-06-01

## article 412



### Inspection Standard of article 412

Parameter	specified value adjacent ISO 105-Fog:2009-05-15
Appearance	plain weave, white, cuts of 5 x 5 cm
Material	according to ISO 105-X12:2016-06-01 cotton 100 %
Mass per unit	according to ISO 3801 g/m <sup>2</sup> 110 ± 2
Whiteness value	according to ISO 105-J02 Y <sub>10</sub> 89 ± 2
Aqueous extract	according to ISO 3071 pH 7.0 ± 0.5

